

# Fluoropolymer Coating Powder

## NEOFLON PFA AC-5539

 TECHNICAL  
DATASHEET

**PFA powder for excellent corrosion resistance.**

### Introduction

- NEOFLON PFA AC-5539 is a PFA powder for electrostatic spraying.
- It easily makes high build black layers displaying excellent corrosion resistance and heat resistance.
- It is good for linings in chemical industry.

### Characteristics

Film appearance	Processing method	Applicable film thickness
Black	Electrostatic spraying	100~1,000μm

### Physical properties of the powder

Items	Unit	Data	Method of measurement
Bulk density	g/ml	0.7	JIS K6891
Average particle size	μm	40	Laser diffraction
Melting point of raw material	°C	305	ASTM D3307
MFR	g/10min	2	ASTM D3307

### Physical properties of the coating film

Items	Unit	Data	Method of measurement
Friction coefficient	-	0.05 – 0.08	Bauden leben steel sheet
Contact angle (Water) (Hexadecane)	degree	102 – 106 65	Contact angle meter at 25°C
Tensile strength	MPa	19.6 – 31.4	JIS K6888
Elongation	%	250 – 350	JIS K6888

\* The numeric values above are typical and not guaranteed.

### Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

For more information, visit our website.

**DAIKIN INDUSTRIES, LTD.**

<https://www.daikinchemicals.com/>

tds-ac-5539-E\_ver01\_Mar\_2018  
Copyright (C) DAIKIN INDUSTRIES, LTD., 2018