

Fluoropolymer Coating Powder NEOFLON PFA AC-5840

 TECHNICAL
DATASHEET

PFA powder for excellent corrosion resistance with rotational molding/lining.

Introduction

- NEOFLON PFA AC-5800 grade is a PFA powder for rotational molding/lining.
- NEOFLON PFA AC-5840 is a PFA powder with lower melt viscosity.
- It makes a clear layer displaying excellent corrosion resistance and heat resistance.
- It is good for linings in chemical industry and semiconductor industry.

Characteristics

Film appearance	Processing method	Applicable film thickness
Clear	Rotational lining /molding,	1,000~2,000μm

Physical properties of the powder

Items	Unit	Data	Method of measurement
Bulk density	g/ml	0.9	JIS K6891
Average particle size	μm	220	Laser diffraction
Melting point of raw material	°C	305	ASTM D3307
MFR of raw material	g/10min	14	ASTM D3307

Physical properties of the coating film

Items	Unit	Data	Method of measurement
Contact angle (Water) (Hexadecane)	degree	109 52	Contact angle meter at 25°C
Tensile strength	MPa	35	ASTM D638
Elongation	%	420	ASTM D638

* The numeric values above are typical and not guaranteed.

Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

<https://www.daikinchemicals.com/>

tds-ac-5840-E_ver01_Mar_2018
Copyright (C) DAIKIN INDUSTRIES, LTD., 2018