

Fluoropolymer

NEOFLON PFA AP-211SH

 TECHNICAL
DATASHEET

NEOFLON PFA AP-211SH is a fully fluorinated high purity PFA. Melt flowability and stress crack resistance are excellent. It is suitable for injection molded parts used for semiconductors.

Introduction

- **AP-211SH** is a copolymer of tetrafluoroethylene and perfluoro alkyl vinyl ether. At the same time, it is a **high purity PFA** with its end groups **completely fluorinated**.
- **Good melt flowability** while maintaining excellent properties of PTFE. It can be used for melt molding as a thermoplastic resin. **Injection molding** and extrusion molding are suitable.
- Excellent in melt flowability. Applicable for injection molded products. It has been used for injection molded parts for semiconductors such as **fitting nuts**.
- **Less eluted fluoride ions**. Due to the fluorinated terminal group.
- **The most excellent stress crack resistance** in injection molding grade of PFA.
- **Excellent chemical resistance** which is not affected by most of the chemicals.
- Flexible and tough under the cryogenic to high temperature.
- Excellent heat resistance. Continuous use temperature is 260 °C.
- **Nonflammable** like POLYFLON PTFE and NEOFLON FEP.
- **Excellent weather resistance**. No properties change even when exposed outside for a long time.

General physical properties

Item	Unit	Value	Test Method
MFR	g/10min	14	372°C、5kgf
Melting Point	°C	303	DSC
Specific Gravity	-	2.14	ASTM D 792 Compliant
Tensile Strength	MPa	35	ASTM D 1708 Compliant
Elongation	%	410	ASTM D 1708 Compliant

* The above values are representative values, not guaranteed values.

Handling method / Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.



| Positively Innovative

Packing specification 25Kg

For more information, visit our website.

DAIKIN INDUSTRIES, LTD.

<https://www.daikinchemicals.com/>

tds-ap-211sh-E_ver01_Mar_2018
Copyright (C) DAIKIN INDUSTRIES, LTD., 2018